



SCHEDA TECNICA FIBRA / FIBER TECHNICAL DATA SHEET

Articolo / Product: Polyester Staple Fiber different colours 30 dtex

Tagli/ Cutlength: 40 45 60 75 90 120 mm

Produttore/Producer: FIBERFIL S.p.A.

Via Serio, 67 (Loc. Mele)

CASNIGO, (BG) ITALY

Proprietà Property	Unità Unit	Nominale Target	Intervallo Range	Metodo Method
Titolo Title	d.tex	30	min. 27 - max. 33	ISO 1973
Tenacità Tenacity	cN/tex	29	min. 24 - max. 34	UNI 5079
Allungamento Elongation	%	80	min. 60 - max. 100	UNI 5079
Ensimaggio Oil pick up	%	0,20	0,10 - 0,30	P.7.6.B
Cretto Crimp frequency	N°/cm	4,0	min. 3,0 - max. 4,0	P.7.6.C
Retrazione a: 180°C Shrinkage at: 180°C	%	< 3,0	< 3,0	P.7.6.A
Resistenza cretto Crimp resistance	%	60	min. 51 - max. 69	P.7.6.E

S.G.Q Signature:

ADDRESS: Fiberfil S.p.A 24020 CASNIGO (BG) Italy - Via Serio, 67 - Località Mele

PHONE: +39 035 741862 - **FAX:** +39 035 741764

WEBSITE: www.fiberfil.it - **E-MAIL:** info@fiberfil.it