



## SCHEDA TECNICA FIBRA / FIBER TECHNICAL DATA SHEET

**Articolo / Product:** Polyester Staple Fiber different colours 3,3 dtex

**Tagli/ Cutlength:** 40 45 60 75 90 120 mm

**Produttore/Producer:** FIBERFIL S.p.A.

Via Serio, 67 (Loc. Mele)

CASNIGO, (BG) ITALY

Proprietà Property	Unità Unit	Nominale Target	Intervallo Range	Metodo Method
Titolo Title	d.tex	3,3	min. 2,9 - max. 3,6	ISO 1973
Tenacità Tenacity	cN/tex	29	min. 24 - max. 34	UNI 5079
Allungamento Elongation	%	70	min. 50 - max. 90	UNI 5079
Ensimaggio Oil pick up	%	0,50	0,40 - 0,60	P.7.6.B
Cretto Crimp frequency	N°/cm	6,5	min. 4,5 - max. 8,5	P.7.6.C
Retrazione a: 180°C Shrinkage at: 180°C	%	< 3,0	< 3.0	P.7.6.A
Resistenza cretto Crimp resistance	%	60	min. 51 - max. 69	P.7.6.E

**S.G.Q Signature:**

**ADDRESS:** Fiberfil S.p.A 24020 CASNIGO (BG) Italy - Via Serio, 67 - Località Mele

**PHONE:** +39 035 741862 - **FAX:** +39 035 741764

**WEBSITE:** www.fiberfil.it - **E-MAIL:** info@fiberfil.it