



## SCHEMA TECNICA FIBRA / FIBER TECHNICAL DATA SHEET

**Articolo / Product:** Polyester Staple Fiber different colours 6,7 dtex

**Tagli/ Cutlength:** 40 45 60 75 90 120 mm

**Produttore/Producer:** FIBERFIL S.p.A.

Via Serio, 67 (Loc. Mele)

CASNIGO, (BG) ITALY

Proprietà Property	Unità Unit	Nominale Target	Intervallo Range	Metodo Method
Titolo Title	d.tex	6,7	min. 6,0 - max. 7,4	ISO 1973
Tenacità Tenacity	cN/tex	29	min. 24 - max. 34	UNI 5079
Allungamento Elongation	%	80	min. 60 - max. 100	UNI 5079
Ensimaggio Oil pick up	%	0,20	0,10 - 0,30	P.7.6.B
Cretto Crimp frequency	N°/cm	5,5	min. 3,5 - max. 7,5	P.7.6.C
Retrazione a: 180°C Shrinkage at: 180°C	%	< 3,0	< 3,0	P.7.6.A
Resistenza cretto Crimp resistance	%	60	min. 51 - max. 69	P.7.6.E

**S.G.Q Signature:**

**ADDRESS:** Fiberfil S.p.A 24020 CASNIGO (BG) Italy - Via Serio, 67 - Località Mele

**PHONE:** +39 035 741862 - **FAX:** +39 035 741764

**WEBSITE:** www.fiberfil.it - **E-MAIL:** info@fiberfil.it